

# CC6400

## STANDARD VOC CLEAR



### PRODUCT DESCRIPTION

Standard VOC Clear CC6400 is a robust clear that can be used for small paint repairs as well as for re-sprays. It has been specially developed for traditional two-coat application and delivers consistent results.

**Robust clearcoat**  
**Consistent quality and productivity**

### FEATURES

- 01** Developed for a traditional two-coat application, but 1.5 coat application is also possible.
- 02** Easy application and consistent result through the use of AZ9100/AZ9101.
- 03** Efficient drying performance.
- 04** Suitable for spot, panel and overall repairs.
- 05** Robust performance.
- 06** Excellent appearance, very good hold out and gloss retention and durability.
- 07** Can be used over all Cromax waterbased and solventbased basecoats.
- 08** Produces a smooth, high-build finish, excellent sagging resistance.

# TECHNICAL DATA SHEET

## CC6400




## STANDARD VOC CLEAR

### Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Cromax Pro Basecoat / Cromax Basecoat: Surfaces must be dried / flashed-off in accordance with TDS before application  
Existing finishes: Surfaces must be sanded and degreased before application



M-6151

	Spot & panel repair		Standard		Large surface	
	Volume	Weight	Volume	Weight	Volume	Weight
CC6400	3	100	3	100	3	100
XK203 *	1	37	-	-	-	-
XK205	-	-	1	37	-	-
XK206	-	-	-	-	1	38
AZ9100 / AZ9101 **	0.2	7	0.2	7	0.2	7

\* XK203 for interiors & spot repair only. No horizontal parts

\*\* AZ9101 can be used at temperatures higher than 30° C



Pot life at 20°C: 1 hr 15 min



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.4	0.7 bar	atomisation pressure

see manufacturer's instructions



2 coats

intermediate and final flash-off: 5 min - 10 min



	XK203	XK205	XK206
60 - 65 °C	25 min	30 min	35 min



Guideline for short wave IR equipment  
Half power: 5 min  
Full power: 10 - 15 min

VOC compliant

2004/42/IIIB(d)(420) 420: The EU limit value for this product (product category: IIB(d)) in ready to use form is maximum 420 g/l of VOC. The VOC content of this product in ready to use form is maximum 420 g/l.

# TECHNICAL DATA SHEET

## CC6400



## STANDARD VOC CLEAR


### Products

CC6400 Standard VOC Clear


XK203 Low Emission Activator Fast  
XK205 Low Emission Activator  
XK206 Low Emission Activator Slow

AZ9100 Performance Agent  
AZ9101 Performance Agent Slow

### Product mix



Mixing ratios with special agents are available in the productmix table on ChromaWeb and in the specific TDS.




ISO 4: 49 - 57 s at 20°C  
DIN 4: 19 - 21 s at 20°C



50 - 60 µm

### Theoretical coverage

450 - 500 m<sup>2</sup>/l at 1 micron dry film thickness  
Due to different activator characteristics and different mixing ratios of the ready-to-use mixture in some TDS versions, the theoretical coverage calculation may vary.  
Note: The practical material consumption depends on several factors, e.g. geometry of the object, surface formation, application method, spray gun setting, inlet pressure, etc.



CC6400 Standard VOC Clear can be overcoated with itself within 24 hours, without intermediate sanding



Clean after use with a suitable solventbased guncleaner.

# TECHNICAL DATA SHEET

**CC6400**



## STANDARD VOC CLEAR

### Remarks

- Material has to be at room temperature (18-25°C) before use.
- Allow additional time for preheating up to panel temperature.
- Surplus ready for use material should not be returned to original can.
- Close can of hardener tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- Close can of Activator tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- Can also be used over activated Centari Basecoat.
- Can also be applied in 1,5 coats, respecting 0-2 min intermediate flash-off and 5-10 min final flash-off.
- For Semi-Flexible systems 10% 805R Flexible Additive can be added to the base material. Activator and Thinner ratios remain equal.
- For Full-Flexible systems the mixing ratios are available in the productmix table on Chromaweb.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Cromax product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Cromax product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.