

799R

VOC SPRAY PUTTY



PRODUCT DESCRIPTION

VOC Spray Putty 799R is a 2K, grey beige finishing spray putty that comes with a peroxide activator. It is recommended for use on bare steel and glass fibre polyester.

FEATURES

- 01 Has a fine homogeneous structure.
- 02 Offers a simple application with good sagging control.
- 03 Delivers high film build.
- 04 Allows for easy sanding, leaving a smooth finish.
- 05 Dries quickly and easily.
- 06 Suitable for IR drying.
- 07 Helps to increase productivity.

TECHNICAL DATA SHEET

799R




VOC SPRAY PUTTY

Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.
Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.
Old or original paintwork well sanded and cleaned.
Fully cured 2K Surfacer or 2K Epoxy Primer-surfacer sanded and cleaned
OEM Primer (e-coat), sanded and cleaned.
Steel, galvanised steel and light aluminium, sanded and cleaned, coated with primer and overcoated with 2K Surfacer



	Volume	Weight
799R	100	100
AXT550 / AXT560	5	3.6



Pot life at 20°C: 20 min



	Spray nozzle	Spray pressure	
Compliant	2 - 2.5	2 - 3 bar	inlet pressure

see manufacturer's instructions



1 - 5 coats

without intermediate flash-off
before bake: 5 min - 10 min



	AXT550 / AXT560
20 °C	2 hr
60 - 65 °C	30 min - 35 min



Guideline for short wave IR equipment
Half power: 10 - 12 min



Coarse sand: P120 - P220
Final sand: P240 - P360



Primer
Primer-Surfacer
Surfacer

VOC compliant

2004/42/IIB(b)(250) 250: The EU limit value for this product (product category: IIB(b)) in ready to use form is maximum 250 g/l of VOC. The VOC content of this product in ready to use form is maximum 250 g/l.

TECHNICAL DATA SHEET

799R




VOC SPRAY PUTTY

Products

799R VOC Spray Putty

AXT550 Hardener For 2K Spray Putty

AXT560 Hardener for 2K Spray Putty



500 - 600 µm film thicknesses up to 1000µm are possible



Clean after use with a suitable solventbased guncleaner.

Remarks

- Material has to be at room temperature (18-25°C) before use.
- Do not apply over 1K primer, etch primer or thermoplastic acrylic finishes.
- Do not wet sand.
- Polyester materials have a limited shelf life. Store in a cool place, and use within 12 months for best results.
- Mix thoroughly by hand before placing the can on mixing machine.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Cromax product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Cromax product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.