

PP0480

SPECIAL PUTTY KIT FOR PLASTIC



PRODUCT DESCRIPTION

Special Putty Kit for Plastic PP0480 is used for the removal of minor surface damages such as scrapes and scratches on all common exterior plastic car parts. The kit is comprised of two products: the black Plastic Putty PP0481 and its dedicated white activator paste, called BPO Hardener.

FEATURES

- 01 Highly flexible after sanding.
- 02 Black putty to match the colour of most exterior plastic parts.
- 03 Easy to apply.
- 04 Pore-free, smooth surface.
- 05 Easy to sand.
- 06 Adheres to all common exterior plastic car parts.

TECHNICAL DATA SHEET

PP0480




SPECIAL PUTTY KIT FOR PLASTIC


Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Repairs to exterior common plastic car parts, sanded and cleaned.
Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.
For best technology properties use of Plastic Primer is preferred. One layer, flash off time 10 minutes at 18-22°C
New exterior common plastic car parts, tempering 60 min. 60-65°C / first cleaning use a pad ultrafine soaked in plastic cleaner / final cleaning use a cloth moistened with plastic cleaner.



	5-35°C
	Weight
PP0481	100
BPO Hardener	2



Pot life at 20°C: 4 min - 6 min




Apply smooth film immediately after mixing, avoiding air entrapment.



	BPO Hardener
20 °C	30 min



P120 - P240
P120 - P240



2K Elastified Surfacers

VOC compliant

2004/42/IIB(b)(250) 240: The EU limit value for this product (product category: IIB(b)) in ready to use form is maximum 250 g/l of VOC. The VOC content of this product in ready to use form is maximum 240 g/l.

TECHNICAL DATA SHEET

PP0480



SPECIAL PUTTY KIT FOR PLASTIC

Products

PLASTIC PUTTY

BPO Hardener



Clean after use with a suitable solventbased cleaning thinner.

Remarks

- Do not add more hardener than recommended to avoid bleeding and spot marking.
- Do not apply over 1K primer, etch primer or thermoplastic acrylic finishes.
- Do not wet sand.
- Clean damaged plastic car substrates carefully, afterwards sand surface damages with P120 - P180.
- Reaction temperature should be at least +5°C.
- In order to obtain very good adhesion properties the use of Plastic Adhesion Promotor 800R/800RA is preferred before applying the putty, 1 coat, flash-off 10 minutes.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Cromax product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Cromax product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.